# INDIANA LIMESTONE - STANDARD GRAY™





LIMESTONE



#### **DESCRIPTION**

This neutral limestone possesses a subdued palette featuring light to medium shades of gray. A restrained, underlying vein pattern and subtle grain movement are visible in the fine to medium grained surface.

### QUARRY OPERATING SINCE | ANNUAL PRODUCTION

1897

12 000 m<sup>3</sup> and more (423 776 cu. ft.)

#### **AVAILABLE FINISHES**

Honed Bush-Hammered Split Face Sandblasted Wire Brushed Tumbled

# **APPLICATIONS**

Exterior Vertical Interior Commercial Horizontal Residential

## PHYSICAL TEST RESULTS

		Imperial	Metric
Absorption by weight	ASTM C97	7.5%	7.5%
Density	ASTM C97	144 lb/ft³	2 306.66 kg/m <sup>3</sup>
Compressive strength	ASTM C170	4 000 Psi	27.58 MPa
Modulus of rupture	ASTM C99	700 Psi	4.83 MPa

#### NATURALLY SUSTAINABLE™

Health Product Declaration® available 2020 ANSI/NSC 373 Certified Quarry since 2018







QUARRY OWNERS | BLOCKS | SLABS | TILES | LANDSCAPING PRODUCTS | CURBS