

POLYCHROME™

● GRANITE



POLISHED

DESCRIPTION

This neutral granite's complexity, resistance and coarse mineral structure make it the choice of architects around the world for huge projects calling for consistency and large volumes.

QUARRY OPERATING SINCE

1968

ANNUAL PRODUCTION

3 000 m³ and more
(106 000 cu. ft.)

AVAILABLE FINISHES


Polished	Waterjet
Antique	Flamed

APPLICATIONS

Exterior	Vertical
Interior	Commercial
Horizontal	Residential

PHYSICAL TEST RESULTS

		Imperial	Metric
Absorption by weight	ASTM C97	0.09%	0.09%
Density	ASTM C97	168.9 lb/ft ³	2 705.52 kg/m ³
Compressive strength	ASTM C170	25 964 Psi	179.02 MPa
Flexural strength	ASTM C880	1 957 Psi	13.48 MPa
Modulus of rupture	ASTM C99	1 825 Psi	12.58 MPa



PROPANE FLAMED



ANTIQUE



QUARRY LOCATION:
La Baie, QC, Canada

NATURALLY SUSTAINABLE™

Health Product Declaration® (HPD) available **2020**



POLYCOR

QUARRY OWNERS | BLOCKS | SLABS | TILES | LANDSCAPING PRODUCTS | CURBS

polycor.com

Computer generated images and printed reproductions may not accurately match natural stone colors.