
ROCHERONS DORÉ[™]

FRENCH LIMESTONE



DESCRIPTION

This fine-grained limestone produces a wide range of earth tones from light beige to warm grey beige, with occasional blush tones in the background. Sandy patterns on the surface create remarkable visual texture.

QUARRY OPERATING SINCE 1893


ANNUAL PRODUCTION 425 m³ and more (14,875 cu. ft.)

AVAILABLE FINISHES Polished Honed	Iron Blasted Bush-Hammered		Tumbled Flamed
APPLICATIONS Exterior Interior	Horizontal Vertical		Commercial Residential
PHYSICAL TEST RESULTS			
		Imperial	Metric
Absorption by weight	ASTM C97	0.40%	0.40%
Density	ASTM C97	165 lb/ft³	2 643 kg/m ³
Compressive strength	ASTM C170	25 972 Psi	179 MPa
Flexural strength	ASTM C880	1 661 Psi	11.46 MPa
Modulus of rupture	ASTM C99	2 329 Psi	16.1 MPa

NATURALLY SUSTAINABLE[™]

Health Product Declaration® available 2020







QUARRY OWNERS | BLOCKS | SLABS | TILES | LANDSCAPING PRODUCTS | CURBS

polycor.com

Computer generated images and printed reproductions may not accurately match natural stone colors.