

ROCHERONS DORÉ™ – FRENCH LIMESTONE

● LIMESTONE



DESCRIPTION

This fine-grained limestone produces a wide range of earth tones from light beige to warm grey beige, with occasional blush tones in the background. Sandy patterns on the surface create remarkable visual texture.

QUARRY OPERATING SINCE

1893

ANNUAL PRODUCTION

425 m³ and more
(14 875 cu. ft.)

AVAILABLE FINISHES

Polished
Honed

Iron Blasted
Bush-Hammered

Tumbled
Flamed

APPLICATIONS

Exterior
Interior
Horizontal


Vertical
Commercial
Residential

PHYSICAL TEST RESULTS

		Imperial	Metric
Absorption by weight	ASTM C97	0.40%	0.40%
Density	ASTM C97	165 lb/ft ³	2 643 kg/m ³
Compressive strength	ASTM C170	25 972 Psi	179 MPa
Flexural strength	ASTM C880	1 661 Psi	11.46 MPa
Modulus of rupture	ASTM C99	2 329 Psi	16.1 MPa

NATURALLY SUSTAINABLE™

Health Product Declaration® available 2020



POLYCOR

QUARRY OWNERS | BLOCKS | SLABS | TILES | LANDSCAPING PRODUCTS | CURBS

polycor.com

Computer generated images and printed reproductions may not accurately match natural stone colors.