



\*Slab Pavers are meant to demonstrate stone appearance and may not necessarily be taken from Polycor Hardscapes & Masonry projects.



\*Computer generated images and printed reproductions may not accurately match natural stone colors.

# CALEDONIA™ GRANITE

Quarried in Riviere-a-Pierre, Quebec, this granite is a true Canadian emblem. Its dark backdrop is mottled with flecks in various shades of taupe and gray. This granite is known for its color consistency, making it an ideal choice for projects to be completed in multiple phases.

## Physical Test Results

		IMPERIAL	METRIC
Absorption by weight	ASTM C97	0.12%	0.12%
Density	ASTM C97	169 lb/ft³	2 710 kg/m³
Compressive Strength	ASTM C170	28 021 Psi	193.2 MPa
Modulus of rupture	ASTM C99	1 711 Psi	11.8 MPa
Flexural strength	ASTM C880	1 392 Psi	9.6 MPa

