

GARDEN WALLS

FULL COLOR BLEND

INDIANA LIMESTONE

HARDSCAPES

& MASONRY



DESCRIPTION

A dry-stacked non-retaining product, limestone walls are ideal for shallow planting beds and as defining landscape elements.

PHYSICAL TEST RESULTS

		Imperial	Metric
Absorption by weight	ASTM C97	7.5%	7.5%
Density	ASTM C97	144 lb/ft ³	2 306.66 kg/m ³
Compressive strength	ASTM C170	4 000 Psi	27.58 MPa
Modulus of rupture	ASTM C99	700 Psi	4.83 MPa

GARDEN WALLS

FINISHES

Front: Split Face
Top & Bottom: Sawn

FORMATS:

Height	Depth	Length
3"	8"	Random*
6"	8"	Random*

*NOTE: Garden Wall is supplied in random lengths, but nominally at approximately 41" long. Supplied stacked on pallet with front, back and sides split faced. Ends may also be sawn finish.



[CONTACT US](#) info@polycor.com | 812 287-7503

WALL CAPS WOODBURY GRAY & FULL COLOR BLEND

■ GRANITE & INDIANA LIMESTONE

HARDSCAPES & MASONRY



DESCRIPTION

Wall caps create a strong and luxurious finish to garden walls and planters. Available in a wide range of sizes with Smooth, Rock or Split Faced edges.

PHYSICAL TEST RESULTS - WOODBURY GRAY

		Imperial	Metric
Absorption by weight	ASTM C97	0.252%	0.252%
Density	ASTM C97	165 ± lb/ft ³	2 643.05 ± kg/m ³
Compressive strength	ASTM C170	17 007 Psi	1 17.26 MPa
Flexural strength	ASTM C880	1 374 Psi	9.5 MPa
Modulus of rupture	ASTM C99	1 617 Psi	1 1.15 MPa

PHYSICAL TEST RESULTS - FULL COLOR BLEND

		Imperial	Metric
Absorption by weight	ASTM C97	7.5%	7.5%
Density	ASTM C97	144 lb/ft ³	2 306.66 kg/m ³
Compressive strength	ASTM C170	4 000 Psi	27.58 MPa
Modulus of rupture	ASTM C99	700 Psi	4.83 MPa

WOODBURY GRAY GRANITE

THICKNESS:

2" & 4"

FINISHES AVAILABLE

Top: Thermal
Edges: Split Face
Bottom: Sawn

FORMATS:

Standard Lengths

4'-0"	7'-0"
5'-0"	8'-0"
6'-0"	

Standard Depths

8"	2'-0"
1'-0"	3'-0"
1'-8"	4'-0"

NOTE: 4" thickness Woodbury Gray granite wall caps only available in 8" and 1'-0" depths.

FULL COLOR BLEND INDIANA LIMESTONE

THICKNESS:

2-1/4" & 3"

FINISHES AVAILABLE

Top, Bottom & Ends: Sawn
Edges: Rock Face

FORMATS:

Length Depth

3'-11 5/8	12"
3'-11 5/8	14"



POLYCOR

CONTACT US info@polycor.com | 812 287-7503

GRANITE EDGING & CURBING WOODBURY GRAY

■ GRANITE

HARDSCAPES & MASONRY



DESCRIPTION

A crisp border for gardens and a strong edge for snow removal, granite edging keeps landscaping manicured and prolongs the life of asphalt.

PHYSICAL TEST RESULTS

		Imperial	Metric
Absorption by weight	ASTM C97	0.252%	0.252%
Density	ASTM C97	165 ± lb/ft ³	2 643.05 ± kg/m ³
Compressive strength	ASTM C170	17 007 Psi	117.26 MPa
Flexural strength	ASTM C880	1 374 Psi	9.5 MPa
Modulus of rupture	ASTM C99	1 617 Psi	11.15 MPa

STEPS

FINISHES AVAILABLE

Top: Thermal
Edges: Split Face

FORMATS - GRANITE EDGING:

Standard Lengths*	Width	Depth
3'-0"	3"	4"
4'-0"	3"	7"
5'-0"	4"	7"
6'-0"	4"	12"

FORMATS - SLOPE CURBING:

Random lengths only from 2'-6" to 10'-0"	Width	Rise
	3-1/2"	11" +/- 1"
	4"	12" +/- 1"
	5"	12" +/- 1"
	6"	12" +/- 1"

Finish: Sawn top
and ends, split face
front & back

FORMATS - STRAIGHT VERTICAL CURBING:

Random lengths only from 4'-0" to 10'-0"	Width	Rise
	4"	17" +/- 1"
	5"	17" +/- 1"
	6"	18" +/- 1"

Finish: Sawn top
and ends, split face
front & back



POLYCOR

*NOTE: Available in additional 1'-0" lengths up to 8'-0".
Most common are 3'-0" to 6'-0" lengths.

CONTACT US info@polycor.com | 812 287-7503

PILLAR CAPS WOODBURY GRAY & FULL COLOR BLEND

■ GRANITE & INDIANA LIMESTONE

HARDSCAPES & MASONRY



DESCRIPTION

Pillar caps create a strong and luxurious finish to garden walls, columns and planters. Available in a wide range of sizes with smooth or rock face edges.

PHYSICAL TEST RESULTS - WOODBURY GRAY

		Imperial	Metric
Absorption by weight	ASTM C97	0.252%	0.252%
Density	ASTM C97	165 ± lb/ft ³	2 643.05 ± kg/m ³
Compressive strength	ASTM C170	17 007 Psi	1 17.26 MPa
Flexural strength	ASTM C880	1 374 Psi	9.5 MPa
Modulus of rupture	ASTM C99	1 617 Psi	1 1.15 MPa

PHYSICAL TEST RESULTS - FULL COLOR BLEND

		Imperial	Metric
Absorption by weight	ASTM C97	7.5%	7.5%
Density	ASTM C97	144 lb/ft ³	2 306.66 kg/m ³
Compressive strength	ASTM C170	4 000 Psi	27.58 MPa
Modulus of rupture	ASTM C99	700 Psi	4.83 MPa

WOODBURY GRAY GRANITE

THICKNESS:

4"

FORMATS:

Width	Depth
24"	24"
26"	26"
32"	32"
36"	36"

FINISHES AVAILABLE

Split Face

FULL COLOR BLEND INDIANA LIMESTONE

THICKNESS:

2-1/4" & 3"

FINISHES AVAILABLE

Rock Face
Square Edge

FORMATS:

Width	Depth
16"	16"
18"	18"
20"	20"
22"	22"
24"	24"
26"	26"
28"	28"
30"	30"



POLYCOR

[CONTACT US](#) | info@polycor.com | 812 287-7503